

Table 2. ICP-MS results from the corrosion product of stem 8

Element	Cr	Co	Zr	Mn	Fe	W	Mo
Concentration (ppm)	114000	11700	142	103	97.2	17.2	8.5