

Passively Q-switched Er-Yb double clad fiber laser with $\text{Cr}^{2+}:\text{ZnSe}$ and $\text{Co}^{2+}:\text{MgAl}_2\text{O}_4$ as a saturable absorber

V. Philippov, J. Nilsson, W. A. Clarkson, A. Abdolvand
*Optoelectronics Research Centre, University of Southampton, Southampton SO17 1BJ, UK,
 phone +44 23 8059 4532, fax +44 23 8059 3142, email vap@orc.soton.ac.uk*

V. E. Kisel, V. G. Shcherbitsky, N. V. Kuleshov
*International Laser Center, 65 ave. F. Scaryny, Minsk 220027, Belarus
 +375-17-2326286, nkuleshov@ilc.by*

V. I. Konstantinov, V. I. Levchenko
*Institute of Solid State and Semiconductor Physics, 17 P. Brovki str., Minsk,
 220027, Belarus*

Passive Q-switching of fiber lasers with saturable absorbers have attracted attention because of simplicity and high efficiency. However, the number of known materials which can be used as a saturable absorber is relatively limited due to the features of fiber lasers. While liquefying gallium mirror, semiconductor structures (SESAM), as well as $\text{Co}^{2+}:\text{ZnSe}$ and $\text{Co}^{2+}:\text{ZnS}$ crystals are recent examples of saturable absorbers that have been used in Q-switched fiber lasers, any new material which can be used for this is still very interesting.

Here we report, for the first time to our knowledge, a cladding-pumped passively Q-switched Er-Yb codoped fiber laser with $\text{Cr}^{2+}:\text{ZnSe}$ and $\text{Co}^{2+}:\text{MgAl}_2\text{O}_4$ as saturable absorbers.

The fiber laser configuration consists of a 5 m circular double-clad Er-Yb codoped fiber and an external cavity. Pump light at 915nm was coupled into the fiber through a perpendicularly cleaved fiber end facet. This also serves as a 4% reflecting, outcoupling, cavity mirror. In the other end of the cavity a lens system and a high-reflection (1550 nm) mirror provided external feedback. The lens system had an intermediate focus, where the saturable absorber was located. The intermediate focus waist diameter was typically 20 μm . We used the same laser configuration for both the $\text{Cr}^{2+}:\text{ZnSe}$ and the $\text{Co}^{2+}:\text{MgAl}_2\text{O}_4$ crystals.

The maximum average output power for both crystals was 1.4 W, for 6.5 W of absorbed pump power. The maximum obtained pulse energy was 18 μJ (45W peak power) with $\text{Cr}^{2+}:\text{ZnSe}$ saturable absorber. Typical pulse duration was 370 – 700 ns. The repetition rate was varied between 20 and 85 kHz.

The maximum pulse energy was 22 μJ (60W peak power) with $\text{Co}^{2+}:\text{MgAl}_2\text{O}_4$ saturable absorber. The pulse duration was 370 – 600 ns. The repetition rate was varied between 15 and 65kHz.

Further details and comparisons of fiber lasers passively Q-switched with $\text{Cr}^{2+}:\text{ZnSe}$ and $\text{Co}^{2+}:\text{MgAl}_2\text{O}_4$ crystals will be presented.