PCCP

ARTICLE TYPE

Cite this: DOI: 00.0000/xxxxxxxxx

Received Date Accepted Date

DOI:00.0000/xxxxxxxxx

Energy Decomposition Analysis Method for Metallic Systems

Han Chen^a and Chris-Kriton Skylaris*^a

In this work, we present the first extension of an energy decomposition analysis (EDA) method to metallic systems. We extend the theory of our Hybrid Absolutely Localized Molecular Orbitals (HALMO) EDA to take into account that molecular orbitals in metallic systems are partially occupied, which is done by weighted orthogonalization (WO) of the molecular orbitals using their associated fractional occupancies as weights in the construction of the projection operators. These operators are needed for the self-consistent field for molecular interaction (SCF MI) computation of the polarization-energy contribution to the interaction. The method gives more weight to orbitals that have higher occupancies and treats each fragment as metallic. The resulting HALMO EDA for metallic systems naturally reduces to the insulator version and produces identical results when applied to an insulating system. We present the theory and implementation details of our new approach, and we demonstrate it with sample calculations of relevance to industrial materials. This work provides a new EDA paradigm and tool for the study and analysis of interactions in metallic systems within large-scale DFT calculations.

1 Introduction

Density-functional theory (DFT) aims to estimate the total energy of a system. Complementing DFT or wave-function methods, the main objectives of energy decomposition analysis (EDA) is to partition the interaction energy of a supermolecule into their chemical origins in a similar vein to mono- and diatomic centers^{1,2} but for fragments containing arbitrary number of atoms instead. Examples of the components of an EDA scheme often include electrostatics, exchange-correlation contributions, polarization, and any other relevant chemical phenomena. Hence, EDA is an analytical tool that partitions the interaction energy into chemically interpretable components.

EDA is a family of decomposition methods, each of which is known as an EDA scheme. EDA schemes can be categorized according to the nature of their underlying theory³, of which there are two major categories: variational-based and perturbationbased. Variational-based schemes are typically derived from the early forms of EDA, where the interaction energy is decomposed by the use of intermediate wave functions. Localized Molecular Orbitals (LMO)⁴, Absolutely Localized Molecular Orbitals (ALMO)⁵, and Block-Localized Wavefunction (BLW)^{6,7} schemes are in this category. Perturbation-based schemes approach EDA from symmetry-adapted perturbation theory (SAPT) scheme^{8,9}, where the interactions among the fragments are seen as perturbations to the non-interacting description and are constructed as corrections resulting from different physical effects. EDA can also facilitate the creation of new force fields in molecular mechanics by parameterization against EDA data, thereby yielding force fields that are more accurate and transferable^{10,11}.

Whenever the interaction energy is concerned, basis set superposition error (BSSE) must be taken into account. There are many approaches to addressing BSSE¹², but a common approach taken by some EDA schemes is the self-consistent field for molecular interaction (SCF MI), which optimizes the molecular orbitals in the presence of all fragments without BSSE¹³. Essentially, SCF MI expands the molecular orbitals of each fragment in the basis functions of the fragment only, which minimizes the amount of charge transfer that occurs among the fragments¹⁴. As such, SCF MI can also be used for computing the energy arising from charge transfer, which is evaluated by taking the difference between applying and not applying SCF MI. In the context of EDA, charge transfer is a useful and interpretable component that indicates the amount of charge that is transferred from one fragment to another⁵. While different approaches to SCF MI have been proposed, the method of localized molecular orbitals (LMO) SCF MI¹⁵ is chosen here for its amenability to fractional occupancies inherent in species with sufficiently small band gaps at finite electronic temperatures.

In the family of finite-temperature DFT methods, various approaches have been employed to study systems under finite electronic temperatures ^{16,17}, at excited states ^{18,19}, or open systems that have fractional electron numbers ²⁰. For the validation of metallic systems presented in this work, the finite-temperature

^a School of Chemistry, University of Southampton, Highfield, Southampton, SO17 1BJ, UK. E-mail: c.skylaris@soton.ac.uk

DFT algorithm of ensemble DFT (EDFT)^{21,22} in the ONETEP software package^{23,24} is used to optimize a set of sample non-excited metallic systems with sufficiently small band gaps that produces fractional occupancies at specific electronic temperatures. Without EDA, metallic systems can be fragmented into subsystems in order to obtain the interaction energy, but nothing beyond such a coarse-grained energy value would be available. EDA methods serve to decompose the interaction energy but are normally developed for the pure state where the occupancies are integral. EDA schemes, particularly those that require SCF MI as in ALMO/HALMO EDA, pose difficulties in decomposing the interaction energy of a metallic system due to the fractional occupancies that are part of the optimization process in EDFT. Hence, fractional occupancies must also be incorporated in the SCF-MI optimization process of the fragmented system.

Although EDA is normally developed and applied to nonconducting species at the pure state, developing EDA for species that have a conduction band or have fragments that interact with each other through the conduction of charge necessitates the incorporation of EDA in EDFT, such that the interactions (which could possibly involve covalent bonding) can be dissected into contributing factors as EDA components. In this work, we present an extended implementation of HALMO EDA that allows it to be incorporated into EDFT for metallic systems at finite electronic temperatures. EDA and EDFT are first given an overview. The problem of extending SCF MI to fractional occupancies in EDA for each fragment with weighted orthogonalization (WO)²⁵ is then discussed. WO is essential in orthogonalizing the molecular orbitals based on their differing fractional occupancies for the projection operators needed by SCF MI. Finally, motivation of and results from EDA with EDFT applied to sample metallic systems with small band gaps are presented.

2 Methods

2.1 Energy Decomposition Analysis

The EDA scheme used in this work is Hybrid Absolutely Localized Molecular Orbitals (HALMO)^{26,27}, which decomposes the interaction energy into three major components based on the firstgeneration ALMO EDA⁵: frozen density, polarization, and charge transfer. Further decomposition of the frozen-density component is based on LMO EDA⁴ and is discussed below. HALMO is a hybrid EDA scheme that has components sharing some names for similar, though not identical, components in LMO, whereas HALMO is compatible with and has the same corresponding component names as ALMO. The interaction energy, ΔE_{int} , is decomposed into the three major components of HALMO EDA as

$$\Delta E_{\rm int} = \Delta E_{\rm frz}^{\rm HALMO} + \Delta E_{\rm pol}^{\rm HALMO} + \Delta E_{\rm ct}^{\rm HALMO}$$
(1)

in the same manner as ALMO EDA. Frozen density, $\Delta E_{\rm frz}^{\rm HALMO}$, is further decomposed as

$$\Delta E_{\rm frz}^{\rm HALMO} = \Delta E_{\rm es}^{\rm HALMO} + \Delta E_{\rm ex}^{\rm HALMO} + \Delta E_{\rm rep}^{\rm HALMO} + \Delta E_{\rm corr}^{\rm HALMO}$$
(2)

and charge transfer is separated into a delocalization term and BSSE correction.

Electrostatics component, ΔE_{es}^{HALMO} , is the change in classicallike terms of the Kohn-Sham (KS) energy containing the Coulombic repulsions when going from isolated fragments to the supermolecule without orbital orthogonalization. Letting Ψ be the wave function of any intermediate quantum state, the electrostatics component is defined ^{4,26} as

$$\Delta E_{\rm es}^{\rm HALMO} = E_{\rm cl} \left[\Psi_{\tilde{X}} \right] - \sum_{J \in \tilde{X}} E_{\rm cl} \left[\Psi_J \right] \tag{3}$$

where $E_{\rm cl}$ is the energy functional for the classical-like part of the KS energy, and \tilde{X} is the set of fragments whose molecular orbitals are localized and variationally optimized within their respective fragments in isolation of other fragments. Exchange component, $\Delta E_{\rm ex}^{\rm HALMO}$, is the change in exchange energy when going from isolated fragments to the supermolecule without orbital orthogonalization. It is defined ^{4,26} as

$$\Delta E_{\text{ex}}^{\text{HALMO}} = E_{\text{x}} \left[\Psi_{\tilde{X}} \right] - \sum_{J \in \tilde{X}} E_{\text{x}} \left[\Psi_J \right]$$
(4)

where E_x is the energy functional for the exchange part of the KS energy. Pauli-repulsion component, ΔE_{rep}^{HALMO} , is the change in energy upon orbital orthogonalization excluding correlation. It is defined ^{4,26} as

$$\Delta E_{\text{rep}}^{\text{HALMO}} = (E_{\text{cl}}[\Psi_{X*}] + E_{x}[\Psi_{X*}]) - (E_{\text{cl}}[\Psi_{\tilde{X}}] + E_{x}[\Psi_{\tilde{X}}])$$
(5)

where X* is the set of fragments whose molecular orbitals are localized and were first variationally optimized within their respective fragments in isolation of other fragments and are then orthogonalized across the supermolecule. Correlation component, $\Delta E_{\rm corr}^{\rm HALMO}$, is the change in correlation energy when going from isolated fragments to the supermolecule with orthogonalized molecular orbitals. It is defined ²⁶ as

$$\Delta E_{\rm corr}^{\rm HALMO} = E_{\rm c} \left[\Psi_{X*} \right] - \sum_{J \in \tilde{X}} E_{\rm c} \left[\Psi_J \right] \tag{6}$$

where E_c is the energy functional for the correlation part of the KS energy.

HALMO polarization component, $\Delta E_{\rm pol}^{\rm HALMO}$, is the change in energy when going from the supermolecule with orthogonalized molecular orbitals to the supermolecule with SCF-MI optimized ^{13–15} molecular orbitals. It is defined ^{5,26} as

$$\Delta E_{\text{pol}}^{\text{HALMO}} = E\left[\Psi_{\widehat{X}}\right] - E\left[\Psi_{X*}\right]$$
(7)

where \widehat{X} is the set of fragments whose molecular orbitals are optimized under SCF-MI constraints. Charge-transfer component, $\Delta E_{\rm ct}^{\rm HALMO}$, is the change in energy when going from the supermolecule with SCF-MI optimized molecular orbitals to the supermolecule with optimized delocalized molecular orbitals. It is defined ^{5,26} as

$$\Delta E_{\rm ct}^{\rm HALMO} = \Delta E_{\rm deloc}^{\rm HALMO} + \Delta E^{\rm BSSE}$$
(8)

where

$$\Delta E_{\rm deloc}^{\rm HALMO} = E\left[\Psi_X\right] - E\left[\Psi_{\widehat{X}}\right] \tag{9}$$

is the delocalization term, *X* is the set of fragments whose molecular orbitals are expanded in all nonorthogonal generalized Wannier functions (NGWFs)²⁸ and variationally optimized across the supermolecule, and $\Delta E^{\rm BSSE}$ is the BSSE-correction term.

To determine the components of HALMO EDA, various quantum states are evaluated that represent the intermediate wave functions used in defining each component. The steps for evaluating such quantum states are depicted in Figure 1.



Fig. 1 Steps for evaluating the quantum states for the corresponding components in HALMO EDA.

2.2 Ensemble DFT

Ensemble DFT (EDFT) as in ONETEP treats a supermolecule as a whole without the concept of fragmentation as in EDA. EDFT involves occupancies that are fractional, since a species is no longer evaluated at the pure state and, hence, the density operator is no longer idempotent. The lack of idempotency complicates SCF MI due to the fact that SCF-MI methods were originally developed under the pervasive assumption of the pure state. Therefore, SCF MI must be extended to include fractional occupancies. Before considering EDFT with fragmentation and under the constraints of SCF MI, an overview of EDFT is given first.

A system of interacting electrons²² satisfies the Kohn-Sham (KS) equation,

$$\hat{H} |\psi_i\rangle = \varepsilon_i |\psi_i\rangle \tag{10}$$

where $\{|\psi_i\rangle\}$ are orthonormalized molecular orbitals, $\{\varepsilon_i\}$ are eigenvalues, and \hat{H} is the Hamiltonian as

$$\hat{H} = \hat{T} + \hat{V}_{\text{ext}} + \hat{V}_{\text{H}}[n] + \hat{V}_{\text{xc}}[n]$$
(11)

 \hat{T} is the kinetic energy operator, \hat{V}_{ext} is the potential operator due to the field of the nucleus, \hat{V}_{H} is the Hartree operator, \hat{V}_{xc} is the exchange-correlation operator, and $n(\mathbf{r}) = \rho(\mathbf{r}, \mathbf{r})$ is the electron density.

The occupancy, f, of a molecular orbital is determined from the

Fermi-Dirac distribution as a function of its orbital energy, ε :

$$f_i(\varepsilon_i;\mu) = \frac{1}{1 + e^{(\varepsilon_i - \mu)/(k_{\rm B}T)}}$$
(12)

where $k_{\rm B}$ is the Boltzmann constant, T is a non-zero electronic temperature, and μ is the Fermi level as a parameter. Also called chemical potential, a Fermi level is determined algorithmically (as in ONETEP²²) from a known number of electrons and a given set of orbital energies. For a fixed set of orbital energies at a specified electronic temperature, the search begins with an initial guess of the Fermi level and calculates the occupancies of the molecular orbitals using Equation (12). If the sum of the occupancies differs from the expected number of electrons, the search adjusts the Fermi level in the appropriate direction and recalculates the occupancies. The algorithm repeats and adjusts the Fermi level until the occupancies computed from the Fermi-Dirac distribution sum to the number of electrons, thereby determining the Fermi level of the species. Fractional occupancies resulting from finite electronic temperature should be distinguished from correlation-induced fractional occupancies in strongly correlated systems. Higher temperature translates to higher kinetic energy of the electrons, causing them to partially occupy orbitals of greater energies. In strongly correlated systems, electrons cannot be treated as non-interacting, since Coulomb repulsion is no longer an insignificant factor and could cause higher energy levels to be partially occupied due to the strong repulsion.

The entropy, \mathcal{S} , depends on the occupancies by

$$\mathscr{S}(\mathbf{f}) = -k_{\mathrm{B}} \sum_{i} \left(f_{i} \ln f_{i} + (1 - f_{i}) \ln (1 - f_{i}) \right)$$
(13)

The Helmholtz free energy, A, relates the KS energy and the entropy via the electronic temperature, T, by

$$A\left[\hat{H},\Psi,\mathbf{f};T\right] = \sum_{i} f_{i}\left\langle\psi_{i}\middle|\hat{T}+\hat{V}_{\text{ext}}\middle|\psi_{i}\right\rangle + E_{\text{H}}\left[n\right] + E_{\text{xc}}\left[n\right] - T\mathscr{S}\left(\mathbf{f}\right)$$
(14)

where *n* is the electron density and is formed from the molecular orbitals, Ψ , and the occupation numbers, **f**. The Helmholtz free energy can be expressed in terms of NGWFs and expansion coefficients as

$$A\left[\hat{H}, \mathbf{M}, \Phi, \mathbf{f}; T\right] = \mathbf{f} \mathbf{M}^{\dagger} \Phi^{\dagger} \left(\hat{T} + \hat{V}_{\text{ext}}\right) \Phi \mathbf{M} + E_{\text{H}}\left[n\right] + E_{\text{xc}}\left[n\right] - T\mathscr{S}\left(\mathbf{f}\right)$$
(15)

where **M** is the expansion coefficient matrix, and $\Phi = (|\phi_1\rangle |\phi_2\rangle \cdots)$ is the NGWFs. Since the Hamiltonian also depends on the density operator, (14) must be evaluated in a self-consistent manner. The density kernel, $\mathbf{K} \equiv \mathbf{MfM}^{\dagger}$, contains the fractional occupation numbers and is used in constructing the density operator as $\Phi \mathbf{K} \Phi^{\dagger}$.

In ONETEP's implementation of EDFT, the Hamiltonian is optimized by a line-search algorithm in the space of Hamiltonian elements²⁹ for a fixed set of NGWFs. Let $\tilde{\mathbf{H}}^{(m)}$ denote the Hamiltonian that is formed from the *m*-th electron density, $n^{(m)}$, whose molecular orbitals were in turn solved from a trial Hamiltonian, $\mathbf{H}^{(m)}$, as

$$\mathbf{H}^{(m)}\mathbf{M}^{(m)} = \mathbf{S}\mathbf{M}^{(m)}\boldsymbol{\varepsilon}^{(m)}$$
(16)

where $\mathbf{H}^{(m)}$ and $\tilde{\mathbf{H}}^{(m)}$ are the matrix representations of the corresponding Hamiltonian in NGWFs, **S** is the overlap matrix of NGWFs, $\mathbf{M}^{(m)}$ is the coefficient matrix for the molecular orbitals expanded in NGWFs, and $\varepsilon^{(m)}$ is a diagonal matrix of eigenvalues. According to the line-search algorithm, the next Hamiltonian is determined by

$$\mathbf{H}^{(m+1)} = \mathbf{H}^{(m)} + \lambda \Delta^{(m)} \tag{17}$$

with the definition of

$$\Delta^{(m)} \equiv \tilde{\mathbf{H}}^{(m)} - \mathbf{H}^{(m)} \tag{18}$$

and λ is a damping parameter fitted against a polynomial such that the Helmholtz free energy is minimized^{21,29}. Equation (17) can then be rewritten as

$$\mathbf{H}^{(m+1)} = (1-\lambda)\mathbf{H}^{(m)} + \lambda \tilde{\mathbf{H}}^{(m)}$$
(19)

The line-search algorithm performs the iterations over *m* until the Liouville equation is satisfied when the commutator, $\left[\mathbf{\tilde{H}}^{(m)}, \mathbf{K}^{(m)}\right]$, attains zero, with the definition of the elements of the density kernel, **K**, as

$$K^{ij} = \sum_{k}^{N_{\text{elec}}} M^{i}_{k} f_{k} \left(\mathbf{M}^{\dagger} \right)_{k}^{j}$$
(20)

2.3 Self-Consistent Field for Molecular Interaction

Basis set superposition error (BSSE) is a problem that has been widely studied with many methods and variations thereof being proposed in eliminating it ^{12,30}. A family of methods for describing and dealing with such error used by some EDA schemes is self-consistent field for molecular interaction (SCF MI)^{13–15,30–33}. SCF MI constructs molecular orbitals using basis functions from each corresponding fragment only, which reduces charge transfer among fragments¹⁴. LMO SCF MI is chosen as the SCF-MI method for HALMO EDA due to its mathematical amenability of incorporating fractional occupancies. For ONETEP, BSSE is not exhibited³⁴, since the NGWFs that ONETEP uses for expanding the molecular orbitals are themselves expanded in terms of a plane-wave basis set defined as periodic sinc (psinc) functions³⁵. The psinc functions homogeneously span the simulation cell and are not biased by the atomic positions. As such for ONETEP, SCF MI is used exclusively for the purpose of separating out the charge-transfer component^{26,36}.

LMO SCF MI¹⁵ uses localized molecular orbitals and constrained minimization of energy to ensure orthogonality within each fragment. It has no relations to LMO EDA⁴. Localized molecular orbitals are expressed as

$$|\psi_{A\alpha}\rangle = \sum_{p} |\phi_{Ap}\rangle M^{Ap}{}_{A\alpha}$$
(21)

where A is a fragment, Ap is the index of a basis function in A, $A\alpha$

is the index of a molecular orbital in A, and

$$M^{Ap}{}_{B\alpha} = \begin{cases} M^{Ap}{}_{A\alpha} & A = B\\ 0 & A \neq B \end{cases}$$
(22)

are the expansion coefficients for some Fragment B.

The lowest energy can be constructed¹⁵ from the molecular orbitals in Equation (21) by evaluating

$$\hat{H} |\psi_{A\alpha}\rangle = |\psi_{A\alpha}\rangle \varepsilon_{A\alpha}$$
 (23)

for each fragment, where $\{\psi_{A\alpha}\}$ are the localized molecular orbitals on Fragment *A*, $\{\varepsilon_{A\alpha}\}$ are the orbital energies as eigenvalues, and \hat{H} is the Hamiltonian. Each dual molecular orbital is defined as

$$\left. \psi^{A\alpha} \right\rangle = \sum_{B\beta} \left| \psi_{B\beta} \right\rangle \left(\sigma^{\mathrm{MI}} \right)^{B\beta,A\alpha}$$
(24)

where

$$\sigma_{\rm MI} = \Psi^{\dagger}_{\rm MI} \Psi_{\rm MI} \tag{25}$$

$$\sigma^{\rm MI} = \sigma_{\rm MI}^{-1} \tag{26}$$

$$\Psi_{\rm MI} = \begin{pmatrix} \Psi_A & \Psi_B & \cdots \end{pmatrix} \tag{27}$$

$$\Psi_J = \left(\begin{array}{cc} |\psi_{J,1}\rangle & |\psi_{J,2}\rangle & \cdots \right)$$
(28)

In LMO SCF MI, $\Psi_J^{\dagger}\Psi_J$ is constrained to be an identity matrix for Fragment *J* for all *J*. The dual molecular orbitals localized to Fragment *J* are expressed as

$$\Psi^{J} = \Psi_{\mathrm{MI}} \left(\sigma^{\mathrm{MI}} \right)_{J} \tag{29}$$

where $(\sigma^{\text{MI}})_J$ is the matrix of column vectors from σ^{MI} that correspond to Fragment *J*. Extending Equation (29) to include all localized molecular orbitals becomes

$$\Psi^{\mathrm{MI}} = \begin{pmatrix} \Psi^{A} & \Psi^{B} & \dots \end{pmatrix}$$
$$= \begin{pmatrix} \Psi_{\mathrm{MI}} (\sigma^{\mathrm{MI}})_{A} & \Psi_{\mathrm{MI}} (\sigma^{\mathrm{MI}})_{B} & \dots \end{pmatrix}$$
$$= \Psi_{\mathrm{MI}} \sigma^{\mathrm{MI}}$$
(30)

Performing LMO SCF MI involves finding the energy minimum using the first derivative of the energy with respect to the expansion coefficients, $\{M^{Jq}_{J\beta}\}^{15}$:

$$\frac{\partial E}{\partial M^{Jq}{}_{J\beta}} = 4f_{J\beta}Y^{Jq}{}_{J\beta} \tag{31}$$

for all J, where

$$Y^{Jq}{}_{J\beta} = \left\langle \phi_{Jq} \right| \left(1 - \hat{P} \right) \hat{H} \left| \psi^{J\beta} \right\rangle$$
(32)

$$\hat{P} = \sum_{i} \left| \psi^{i} \right\rangle \left\langle \psi_{i} \right| = \sum_{i} \left| \psi_{i} \right\rangle \left\langle \psi^{i} \right|$$
(33)

$$= \Psi^{MI} \Psi^{\dagger}_{MI} = \Psi_{MI} \Psi^{MI\dagger}$$
$$= \Psi_{MI} \sigma^{MI} \Psi^{\dagger}_{MI}$$
(34)

and $f_{J\beta}$ is the occupancy of $\psi_{J\beta}$. The stationary point can be determined by solving an eigenvalue problem casted from Equation (31) set to 0. By solving an eigenvalue problem, molecular orbitals and their orbital energies are obtained, and an effective Hamiltonian can then be constructed from the projection operators. The process repeats until the energy is minimized (Figure 2). This allows solving the expansion coefficients, \mathbf{M}_J , for the molecular orbitals localized to Fragment *J* to be part of the optimization process.

Attaining the energy minimum results in Equation (31) becoming zero:

$$Y^{Jq}{}_{J\beta} = 0 \tag{35}$$

which can be extended to all dual molecular orbitals localized to Fragment *J* as

$$\Phi_J^{\dagger} \left(1 - \hat{P} \right) \hat{H} \Psi^J = \mathbf{0} \tag{36}$$

To rewrite Equation (36) as an eigenvalue problem with an effective Hamiltonian that is Hermitian, the partial projection operator for Fragment J is defined as

$$\hat{P}^{J} \equiv \sum_{i} \left| \Psi^{Ji} \right\rangle \langle \Psi_{Ji} | = \Psi^{J} \Psi_{J}^{\dagger}$$
(37)

and has the property that

$$\hat{P}^{J}\Psi^{K} = \begin{cases} \Psi^{J} & J = K\\ \mathbf{0} & J \neq K \end{cases}$$
(38)

for some Fragment *K*. Using the partial projection operator, the effective Hamiltonian for Fragment J in LMO SCF MI¹⁵ is

$$\hat{H}^{J} = \left(1 - \hat{P} + \hat{P}^{J\dagger}\right) \hat{H} \left(1 - \hat{P} + \hat{P}^{J}\right)$$
(39)

whose matrix representation ³⁷ in NGWFs can be obtained by distributing the operators on the right-hand side and then multiplying by Φ_I^{\dagger} and Φ_J from the left and right, respectively:

$$\tilde{\mathbf{H}}^{J} = \Phi_{J}^{\dagger} \hat{H}^{J} \Phi_{J} = \mathbf{H}_{J} - \mathbf{H}_{J \bullet} \mathbf{D} \mathbf{S}_{\bullet J} + \mathbf{H}_{J \bullet} \mathbf{D}_{J} \mathbf{S}_{J}$$

$$- \mathbf{S}_{J \bullet} \mathbf{D} \mathbf{H}_{\bullet J} + \mathbf{S}_{J \bullet} \mathbf{D} \mathbf{H} \mathbf{D} \mathbf{S}_{\bullet J} - \mathbf{S}_{J \bullet} \mathbf{D} \mathbf{H} \mathbf{D}_{J} \mathbf{S}_{J} \qquad (40)$$

$$+ \mathbf{S}_{J}^{\dagger} \mathbf{D}_{J}^{\dagger} \mathbf{H}_{\bullet J} - \mathbf{S}_{J}^{\dagger} \mathbf{D}_{J}^{\dagger} \mathbf{H} \mathbf{D} \mathbf{S}_{\bullet J} + \mathbf{S}_{J}^{\dagger} \mathbf{D}_{J}^{\dagger} \mathbf{H} \mathbf{D}_{J} \mathbf{S}_{J}$$

with the definitions of

$$\mathbf{H}_{J\bullet} \equiv \Phi_{J}^{\dagger} \hat{H} \Phi \tag{41}$$

$$\mathbf{H}_{\bullet J} \equiv \Phi^{\dagger} \hat{H} \Phi_J \tag{42}$$

$$\mathbf{D} \equiv \mathbf{M}_{\mathrm{MI}} \boldsymbol{\sigma}^{\mathrm{MI}} \mathbf{M}_{\mathrm{MI}}^{\dagger} \tag{43}$$

$$\mathbf{D}_{J} \equiv \mathbf{M}_{\mathrm{MI}} \left(\boldsymbol{\sigma}^{\mathrm{MI}} \right)_{J} \mathbf{M}_{J}^{\dagger} \tag{44}$$

During the line-search algorithm of EDFT, the constrains of SCF MI are imposed, thereby affecting the search direction in the Hamiltonian space and, in turn, the molecular orbitals solved from it (Figure 2). The resulting molecular orbitals, expanded in the NGWFs of the corresponding fragments, would therefore satisfy the constraints of SCF MI. Along with the fractional occupancies determined from the Fermi-Dirac distribution during the line search of EDFT, the density kernel can thus be constructed and used in calculating the electron density.

2.3.1 Incorporating Fractional Occupancies

Many EDA schemes were developed for the pure state. By assuming the pure state, an EDA scheme and its implementation can simplify what otherwise could be a complicated scheme. Recent developments of the ALMO EDA scheme allow for excited systems³⁸ but involves accommodating the EDA components for the system at an excited state into the same EDA scheme by including a difference term for each EDA component. While this has advantages such as being able to compare the same system at pure and excited states, it introduces complexities to an existing EDA scheme in the interpretation and in the implementation. While excited systems are not studied in this work, EDA with EDFT is applied to systems in ensemble states at finite electronic temperatures without modifying the EDA scheme itself.

For incorporating ensemble-state calculations into EDA, the fractional occupancies that are part of the density kernel are included in the implementation of SCF MI. The problem of performing ensemble-state calculations as part of an EDA scheme then becomes a problem of determining the fractional occupancies during the energy decomposition. Determining the fractional occupancies themselves is performed by the existing implementation of EDFT in ONETEP²² using the Fermi-Dirac distribution, and the HALMO-EDA scheme itself remains unmodified with the same components.

The density kernel varies depending on the quantum state of the system. Specifically, the molecular orbitals differ via the expansion coefficients, and the molecular orbitals would have another set of orbital energies. In turn, occupancies depend on the orbital energies^{22,39,40}. Therefore, the density kernel must be reconstructed along with a changing set of occupancies throughout an EDA calculation. According to the Fermi-Dirac distribution for fragmented systems, the occupancy, f_{Ji} , of a molecular orbital localized to Fragment J as a function of its orbital energy, ε_{Ji} , is

$$f_{Ji} = f(\varepsilon_{Ji}; \mu_J) = \frac{1}{e^{(\varepsilon_{Ji} - \mu_J)/(k_{\rm B}T)} + 1}$$
(45)

where μ_J is the Fermi level of Fragment *J* as the parameter. The

number of electrons in each fragment is known from the optimization of the fragments in isolation. For each fragment, its own Fermi level is determined, followed by calculating the desired occupancies. By evaluating the Fermi-Dirac distribution for each fragment, the SCF-MI constraint of disallowing charge transfer to take place is satisfied, and the occupancies of the molecular orbitals in a fragment are calculated without the orbital energies from other fragments. The process of incorporating occupancies from EDFT in SCF MI is diagrammed in Figure 2.



Fig. 2 LMO SCF MI with occupancies from EDFT. EDFT uses the Fermi-Dirac distribution to calculate the occupancies of the molecular orbitals. Once calculated, the occupancies are incorporated into the density kernel. From the density kernel and occupancies, the internal and Helmholtz energies are evaluated. The Helmholtz energy is used in the line search of EDFT to find the energy minimum.

2.4 Weighted Orthogonalization

Treating all molecular orbitals equally during orthogonalization would be inconsistent with their relative importance. Some of the orthogonalized molecular orbitals should take higher priority in minimizing their displacements from their nonorthogonalized counterparts in a least-squares fashion. Such orthogonalization can be done using weighted orthogonalization (WO)²⁵. The priority of a molecular orbital in relation to others depends on the context and the application. In this work, molecular orbitals are orthogonalized using occupation numbers as weights.

WO is a two-step process. First step is the preliminary orthogonalization of molecular orbitals, $\{|f_i\rangle\}$ (not occupation numbers), without weights using symmetric orthogonalization to yield an intermediate set of molecular orbitals, $\left\{ \left| g'_{j} \right\rangle \right\}$. Second step orthogonalizes the intermediate set such that the weighted overlap sum, OVLPS, is maximized:

$$OVLPS = \sum_{i} w_i \langle f_i | g_i \rangle \tag{46}$$

where w_i is the *i*-th weight for $|f_i\rangle$, and $\{|g_j\rangle\}$ is the set of weight-orthogonalized molecular orbitals. Maximizing OVLPS is achieved by performing sweeps of Givens rotations until no rotations are needed based on a threshold. (46) is essentially a reformulation of the least-squares problem for orbitals with weights.

 $\{ |g_j\rangle \}$ are the unknowns and can be expressed in terms of the known intermediate set, $\{ |g'_j\rangle \}$. For a pair of molecular orbitals, the Givens rotation angle, θ , is

$$\begin{pmatrix} |g_k\rangle \\ |g_\ell\rangle \end{pmatrix} = \begin{pmatrix} \cos\theta & -\sin\theta \\ \sin\theta & \cos\theta \end{pmatrix} \begin{pmatrix} |g'_k\rangle \\ |g'_\ell\rangle \end{pmatrix}$$
(47)

$$= \begin{pmatrix} |g'_{k}\rangle\cos\theta - |g'_{\ell}\rangle\sin\theta \\ |g'_{k}\rangle\sin\theta + |g'_{\ell}\rangle\cos\theta \end{pmatrix}$$
(48)

which can be multiplied by the nonorthogonal counterparts with weights to obtain the weighted overlap sum for the pair, $OVLPS_{k\ell}$:

$$OVLPS_{k\ell} = \begin{pmatrix} w_k \langle f_k | & w_\ell \langle f_\ell | \end{pmatrix} \begin{pmatrix} |g_k \rangle \\ |g_\ell \rangle \end{pmatrix}$$
$$= \begin{pmatrix} w_k \langle f_k | & w_\ell \langle f_\ell | \end{pmatrix} \begin{pmatrix} |g'_k \rangle \cos \theta - |g'_\ell \rangle \sin \theta \\ |g'_k \rangle \sin \theta + |g'_\ell \rangle \cos \theta \end{pmatrix} \quad (49)$$
$$= w_k \langle f_k | g'_k \rangle \cos \theta - w_k \langle f_k | g'_\ell \rangle \sin \theta$$
$$+ w_\ell \langle f_\ell | g'_k \rangle \sin \theta + w_\ell \langle f_\ell | g'_\ell \rangle \cos \theta$$

Factoring by the trigonometric functions gives

$$OVLPS_{k\ell} = B_{k\ell}\cos\theta + C_{k\ell}\sin\theta \tag{50}$$

where

$$B_{k\ell} = w_k \left\langle f_k \middle| g'_k \right\rangle + w_\ell \left\langle f_\ell \middle| g'_\ell \right\rangle \tag{51a}$$

$$C_{k\ell} = w_{\ell} \left\langle f_{\ell} \big| g'_{k} \right\rangle - w_{k} \left\langle f_{k} \big| g'_{\ell} \right\rangle$$
(51b)

By using the trigonometric identity

$$\cos\left(\theta - \gamma\right) = \cos\theta\cos\gamma + \sin\theta\sin\gamma \tag{52}$$

the two terms in (50) can be combined into one by multiplying (52) by $A_{k\ell}$ and comparing with it:

$$OVLPS_{k\ell} = A_{k\ell}\cos\left(\theta - \gamma\right) \tag{53}$$

where

$$\cos\gamma = \frac{B_{k\ell}}{A_{k\ell}} \tag{54}$$

$$\sin\gamma = \frac{C_{k\ell}}{A_{k\ell}} \tag{55}$$

$$A_{k\ell} = \sqrt{B_{k\ell}^2 + C_{k\ell}^2}$$
(56)

OVLPS_{$k\ell$} is maximized when $\theta = \gamma$ in (53). cos γ and sin γ are used to construct the rotation matrix in (47) to determine $|g_k\rangle$ and $|g_\ell\rangle$. Givens rotations occur in sweeps, where each sweep is a sequence of (47) for all combinations of *k* and ℓ , and the process repeats until no more rotations are needed in a sweep. The algorithm for weighted orthogonalization and its parallelization are described by Algorithms 1 and 2.

	Algorithm	2	Parallelization	of	Weighted	Orthog	gonalization
--	-----------	---	-----------------	----	----------	--------	--------------

$$\begin{split} \Psi_{0} &\leftarrow \text{nonorthogonal orbitals} \\ \Psi_{1} &\leftarrow \text{symmetric orthogonalization of } \Psi_{0} \\ n &\leftarrow 2 \\ \hline \textbf{repeat} \\ \Psi_{n} &\leftarrow \text{super-step } \Psi_{n-1} \\ \left(\Psi_{a} \quad \Psi_{b} \quad \cdots\right) &\leftarrow \text{partition } \Psi_{n} \\ \textbf{for } \alpha &= a \textbf{ to } N_{\text{partitions }} \textbf{ do} \\ \Psi_{\alpha} &\leftarrow \text{weight-orthogonalize } \Psi_{\alpha} \\ \textbf{end for} \\ \Psi_{n} &\leftarrow \text{sort } \Psi_{n} \textbf{ to original order} \\ n &\leftarrow n+1 \\ \textbf{until } \|\Psi_{n-1} - \Psi_{n-2}\| &< \delta \end{split}$$

Expressing $B_{k\ell}$ and $C_{k\ell}$ in terms of NGWFs, Φ , (51) can be written as

$$B_{k\ell} = w_k \mathbf{m}_{f_k}^{\dagger} \Phi^{\dagger} \mathbf{g}'_k + w_{\ell} \mathbf{m}_{f_{\ell}}^{\dagger} \Phi^{\dagger} \mathbf{g}'_{\ell}$$
(57)

$$C_{k\ell} = w_{\ell} \mathbf{m}_{f_{\ell}}^{\dagger} \Phi^{\dagger} \mathbf{g}_{k}' - w_{k} \mathbf{m}_{f_{k}}^{\dagger} \Phi^{\dagger} \mathbf{g}_{\ell}'$$
(58)

where $\mathbf{g}' = \Phi \mathbf{M}_f \left(\mathbf{M}_f^{\dagger} \mathbf{S} \mathbf{M} \right)^{-\frac{1}{2}}$, \mathbf{g}'_j is the *j*-th preliminarily sym-

metrically orthonormalized molecular orbital, \mathbf{m}_{f_j} is the column matrix of coefficients in the expansion of NGWF for $|f_j\rangle$, \mathbf{M}_f is the expansion coefficients for all nonorthogonalized molecular orbitals, $\mathbf{S} = \Phi^{\dagger} \Phi$ is the overlap matrix of NGWFs, and f_j is again the *j*-th nonorthogonalized molecular orbital and not an occupation number.

3 Results and Discussion

HALMO EDA with EDFT was performed for Pt_{13} -CO(atop), Pt_{55} -CO(atop), anatase- Pt_{13} -CO(atop), Pt_{210} -phenol, and Li_{12} -graphite. These systems have sufficiently small band gaps that they exhibit fractional occupancies at finite electronic temperatures and, therefore, serve as test systems for HALMO EDA with EDFT. All systems were analyzed at the electronic temperature of 0.1 eV except Pt_{210} -phenol, which was analyzed at the electronic temperature of 1000 K. Furthermore, in relevance to the interactions that occur in heterogeneous catalysis, fragmentation of each system for EDA occurs at the bonds between the adsorbate and the catalyst.

The frozen-density component of HALMO EDA contains electrostatics, exchange, Pauli repulsion, and correlation as its subcomponents. For all species in this study, the frozen-density components exhibit similar characteristics. Energy values of electrostatics, exchange, and correlation are negative, indicating that the interactions from these factors are favorable. Energy values of Pauli repulsion, however, are positive and large, which stems from the unfavorable exclusion repulsions caused by overlapping molecular orbitals.

For Pt₁₃-CO(atop), Pt₅₅-CO(atop), and anatase-Pt₁₃-CO(atop), a carbon-monoxide molecule is bonded to the platinum portion of the system. In anatase-Pt₁₃-CO(atop), the platinum nanoparticle is supported by titanium dioxide (TiO₂, also called titania)⁴¹. These systems are depicted in Figure 3. HALMO EDA at an electronic temperature of 0.1 eV was performed for each of the species fragmented at the bond between carbon monoxide and the platinum nanoparticle (Table 1) except anatase-Pt13-CO(atop), which has an additional fragmentation scheme between the platinum nanoparticle and the anatase support (Table 2). HALMO-EDA results for these systems demonstrate some trends among them (Table 1). Unlike Helmholtz interaction energy, internal interaction energy does not contain the entropic term due to temperature. As such, any fractional occupancies result in the two types of interaction energies being different. Indeed, the three platinum species are expected to have fractional occupancies at the specified finite electronic temperature and have unequal internal and Helmholtz interaction energies. From SCF MI, the large charge-transfer energies suggest that the covalency between the carbon monoxide and the platinum are substantial⁵, which is to be expected for heterogeneous catalysis in general.

To get a sense of the charge distribution in relation to the charge-transfer energy, Mulliken population analysis was also performed for each of the platinum-nanoparticle systems in the last part of their respective calculations where charge transfer has occurred (Table 3). Charges of the atoms in each subspecies were summed to give the charge of the subspecies. For the HALMO polarized state from SCF MI, the Mulliken charge of each fragment is zero (data not shown), which is in accordance with a constraint of SCF MI where the delocalization of electrons among fragments is disallowed. Pt_{13} -CO(atop) has a charge-transfer energy of -92.2 kcal/mol, and Pt_{55} -CO has a less negative value of -89.0 kcal/mol. This correlates with the Mulliken charge of carbon monoxide not being as negative in Pt_{55} -CO(atop) (-0.126) as compared to Pt_{13} -CO(atop) (-0.130). Anatase- Pt_{13} -CO(atop), however, does not agree with the trend. A possible explanation is that some of the charge has transferred from anatase to carbon monoxide and made the covalent bonding between carbon monoxide and the platinum nanoparticle less stable. If instead the fragmentation is between the platinum nanoparticle and anatase (Table 2), the charge-transfer energy is much more negative than any of the species in Table 1, and the Mulliken charge on anatase agrees with the charge-transfer energy being more negative.



Fig. 3 $Pt_{13}\text{-}CO(atop), Pt_{55}\text{-}CO(atop),$ and anatase- $Pt_{13}\text{-}CO(atop).$ Red atom is oxygen, light blue atom is carbon, gold atom is platinum, and pink atom is titanium.

Visualizing the major EDA components can be done with electron-density differences (EDD)⁴². Figure 4 illustrates the polarization and charge-transfer components for Pt₁₃-CO(atop). Polarization can be thought of as the change in quantum state where the fragments in the supermolecule are preparing for electron transfer among each other. This can be visualized as an increase in the electron density close to the nucleophilic carbon atom on the side facing the electrophilic platinum atom. During charge transfer, the region between the carbon atom and the platinum atom experiences an increase in electron density as the two atoms form a covalent bond. A corresponding decrease in electron density is observed at the face of the carbon atom, indicating that the electrons migrated from the carbon atom toward the bonding region with the platinum atom. This suggests that the energy decomposition of Pt13-CO(atop) is qualitatively reasonable with the covalency between the Pt nanoparticle and carbon monoxide.

Pt₂₁₀-phenol is another heterogeneous catalysis system (Figure 5) that was tested with HALMO EDA at an electronic temperature of 1000 K (Table 4). Fragmentation is along the binding between Pt₂₁₀ (the slab) and phenol (the adsorbate). Similar to the other systems tested, Pt₂₁₀-phenol exhibits large negative chargetransfer energy (-238.1 kcal/mol) according to HALMO EDA, indicating that there is significant transfer of electrons and, hence, covalency between the two fragments. The relatively small difference (1.3 kcal/mol) between the internal and Helmholtz interaction energies implies that the interaction due to entropic effects from electronic temperature is not very substantial. This in turn



Fig. 4 Difference in electron densities for polarization (left) and for charge transfer (right) of Pt₁₃-CO(atop). Red atom is oxygen, light blue atom is carbon, and gold atom is platinum. Red wireframe indicates an increase in electron density; blue wireframe, decrease. Isovalue is set at $\pm 0.05\,\text{e}\,\text{\AA}^{-3}$.

indicates that the interaction between Pt_{210} and phenol stems significantly from their binding. From this HALMO EDA, the improvement of a catalysis system similar to Pt_{210} -phenol would benefit from optimizing the interaction between the slab and the adsorbate such that the interaction is more favorable for catalysis.



Fig. 5 Pt₂₁₀-phenol with its periodic unit cell.

As a final example, HALMO EDA with EDFT of lithium nucleation at graphite models of battery electrodes was performed. Lithium metal plating is an undesired side effect in lithium-ion cells and decreases the lifetime of the battery⁴³. Plating is caused by the nucleation of lithium ions on the graphite. Increasing the nucleation barrier would be desirable in the design of lithium-ion cells so that a battery's lifetime can be improved. Since lithium nucleation can be viewed as an interaction between lithium ions and graphite, EDA is suitable for examining the factors that contribute to such interaction and could offer some insight on which factors are more prevalent compared to others, otherwise the overall interaction energy would be too coarse-grained. Furthermore, competing designs of lithium-ion cells can also be compared using EDA as part of a methodology that aims to increase the nucleation barrier where some of the EDA components could have an effect on the overall lifetime.

Table 5 lists the HALMO-EDA components of graphite and a cluster of 12 lithium atoms (Figure 6) in vacuum, with graphite as one fragment and the lithium cluster as the other. Similar to the

Table 1 HALMO EDA	with EDFT of Pt ₁₃ -CO(atop),	Pt ₅₅ -CO(atop), and a	natase-Pt ₁₃ -CO(atop) using the RPBE exchange-	correlation functional at
electronic temperature	of 0.1 eV. Fragmentation is in	dicated by the bracketi	ng. All energy values	are in kcal/mol.	
-	FDA Component	[Pt _e][CO(Atop)]	$[Pt_{-}][CO(Atop)]$	[Anatase-Ptro][CO(Aton)]	-

EDA Component	[Pt ₁₃][CO(Atop)]	[Pt ₅₅][CO(Atop)]	[Anatase-Pt ₁₃][CO(Atop)]
Electrostatics	-36.1	-38.3	-39.7
Exchange	-56.3	-53.9	-56.6
Pauli repulsion	214.2	216.9	220.1
Correlation	-22.1	-22.1	-22.8
Polarization	-78.2	-68.4	-45.6
Charge transfer	-92.3	-90.9	-87.8
Internal interaction energy	-70.9	-56.7	-32.5
Helmholtz interaction energy	-67.5	-54.0	-30.5

Table 2 HALMO EDA with EDFT of anatase- Pt_{13} -CO(atop) using the RPBE exchange-correlation functional at electronic temperature of 0.1 eV. Fragmentation is between the platinum nanoparticle and the anatase support, indicated by the bracketing. All energy values are in kcal/mol.

EDA Component	[Anatase][Pt ₁₃ -CO(Atop)]
Electrostatics	-130.0
Exchange	-87.2
Pauli repulsion	418.2
Correlation	-61.0
Polarization	-88.6
Charge transfer	-145.2
Internal interaction energy	-93.9
Helmholtz interaction energy	-92.4

Table 3 Mulliken population analyses of Pt_{13} -CO(atop), Pt_{55} -CO(atop), and anatase- Pt_{13} -CO(atop) for the optimized supermolecule state after charge transfer has occurred.

Subspecies	Pt ₁₃ -CO(Atop)	Pt ₅₅ -CO(Atop)	Anatase-Pt ₁₃ -CO(Atop)
Carbon Monoxide	-0.130	-0.126	-0.137
Platinum Nanoparticle	0.130	0.126	0.558
Anatase	N/A	N/A	-0.421

Table 4 HALMO EDA with EDFT of Pt_{210} -phenol using the optB88 exchange-correlation functional at electronic temperature of 1000 K. Fragmentation is indicated by the bracketing. All energy values are in kcal/mol.

EDA Component	[Pt ₂₁₀][Phenol]
Electrostatics	-139.3
Exchange	-307.7
Pauli repulsion	756.6
Correlation	-39.0
Polarization	-147.8
Charge transfer	-238.1
Internal interaction energy	-115.3
Helmholtz interaction energy	-114.0

other species in this work, the Li₁₂-graphite system exhibits large negative charge-transfer energy (-308.8 kcal/mol) from the interaction between the graphite and lithium cluster. The possibility of making the charge-transfer component less negative could suggest a candidate design that can mitigate the lithium-nucleation effect, which in turn cannot be gleaned from the interaction energy alone. Effects of the finite electronic temperature (0.1 eV) are also exhibited in the difference of 13.7 kcal/mol between internal (-230.6 kcal/mol) and Helmholtz (-216.9 kcal/mol) interaction energies. Electronic temperature lessens the interaction between the lithium ions and graphite due to entropic effects.



Fig. 6 Li₁₂-graphite.

4 Conclusions

We have extended energy decomposition analysis (EDA) methods to metallic systems using a modified version of ONETEP that can dissect the interaction energy of a species at an ensemble state. EDA and self-consistent field for molecular interaction (SCF MI) methods have usually been developed and applied to systems at the pure state. In this work, EDA and SCF MI were expanded to species that are studied with ensemble DFT (EDFT).

SCF MI was combined with EDFT by removing the assumptions of the pure state and incorporating fractional occupancies into the implementation of SCF MI. Fractional occupancies determined by EDFT are normally for the supermolecule as a whole using the Fermi-Dirac distribution. However, in order for SCF MI to accommodate the occupancies into its process, the evaluation of Fermi-Dirac distribution was restricted to individual fragments, resulting in each fragment having a different Fermi level.

Throughout the line search of EDFT in finding the minimum energy, the constraints of SCF MI were imposed such that the molecular orbitals and the associated orbital energies are solved from the effective Hamiltonian of LMO SCF MI¹⁵. The effective Hamiltonian of LMO SCF MI contains projection operators that require weighted orthogonalization (WO) to be constructed due to the fractional occupancies from the ensemble state. Constructing the projection operators was adapted to orthogonalizing the molecular orbitals with fractional occupancies as orthogonalization weights. Using WO, the construction of such SCF-MI projection operators and the level of occupancy of each molecular orbital are therefore made consistent in the formulation and implementation of SCF MI.

The adaptations of EDA and SCF MI to metallic systems were validated using samples from catalysis and batteries, such as carbon-monoxide-bound platinum nanoparticle systems (in vacuum and supported on titania), platinum slab with phenol adsorbed, and graphite with lithium cluster that have sufficiently small band gaps. Across these sample metallic systems, HALMO EDA has provided reasonable decompositions of interactions energies and revealed some trends from SCF MI that correlate with charge distributions and chemical intuition.

This work has provided a new paradigm and tool for the study and analysis of metallic systems using a combination of EDA and EDFT within large-scale quantum chemistry calculations. HALMO EDA has shown to be a useful tool in decomposing the interaction energy into components for comparisons and analysis of systems at ensemble states that require EDFT. It has been demonstrated by this work that EDA with SCF MI can be extended and applied to metallic systems at finite electronic temperatures. With such advancement, EDA and SCF MI are no longer restricted to species at the pure state. Future work can involve more in-depth study of the nature of interactions in some technologically important systems, such as conductors, semiconductors, heterogeneous catalysts, and lithium-ion batteries.

5 Conflicts of Interest

There are no conflicts of interest to declare.

6 Acknowledgements

The authors acknowledge the use of the IRIDIS 5 High Performance Computing Facility, and associated support services at the University of Southampton. The authors are also grateful for computational support from the UK Materials and Molecular Modelling Hub, which is partially funded by EPSRC (EP/T022213/1). This work is part of University of Southampton's Centre for Doctoral Training in Next Generation Computational Modelling (NGCM).

Notes and references

- 1 I. Mayer, Chemical Physics Letters, 2000, 332, 381–388.
- 2 I. Mayer, Chemical Physics Letters, 2003, 382, 265-269.
- 3 M. J. S. Phipps, T. Fox, C. S. Tautermann and C.-K. Skylaris, *Chem Soc Rev*, 2015, **44**, 3177–3211.
- 4 P. Su and H. Li, *The Journal of Chemical Physics*, 2009, **131**, 014102–1–014102–15.
- 5 R. Khaliullin, E. Cobar, R. Lochan, A. Bell and M. Head-Gordon, *The Journal of Physical Chemistry*, 2007, **111**, 8753– 8765.
- 6 Y. Mo, J. Gao and S. D. Peyerimhoff, J. Chem. Phys., 2000, 112, 5530–5538.
- 7 Y. Mo, P. Bao and J. Gao, *Phys. Chem. Chem. Phys.*, 2011, **13**, 6760–6775.
- 8 B. Jeziorski, R. Moszynski and K. Szalewicz, *Chem. Rev.*, 1994, 94, 1887–1930.
- 9 K. Patkowski, WIREs Comput Mol Sci, 2020, 10, e1452.
- 10 J. McDaniel and J. Schmidt, Annual Review of Physical Chemistry, 2016, 67, 467–488.
- 11 R. Qi, Q. Wang and P. Ren, *Bioorganic & Medicinal Chemistry*, 2016, 24, 4911–4919.
- 12 M. Gutowski and G. Chałasiński, J. Chem. Phys., 1993, 98, 5540–5554.
- 13 E. Gianinetti, M. Raimondi and E. Tornaghi, *International Journal of Quantum Chemistry*, 1996, **60**, 157–166.

Table 5 HALMO EDA with EDFT of Li_{12} -graphite in vacuum using the PBE exchange-correlation functional at electronic temperature of 0.1 eV. Fragmentation is indicated by the bracketing. All energy values are in kcal/mol.

EDA Component	[Li ₁₂][Graphite]
Electrostatics	-298.9
Exchange	-288.4
Pauli repulsion	951.4
Correlation	-59.5
Polarization	-170.1
Charge transfer	-308.8
DFT-D2	-56.2
Internal interaction energy	-230.6
Helmholtz interaction energy	-216.9

- 14 T. Nagata, O. Takahashi, K. Saito and S. Iwata, *Journal of Chemical Physics*, 2001, **115**, 3553–3560.
- 15 H. Stoll, G. Wagenblast and H. Preuβ, Theoretica Chimica Acta, 1980, 57, 169–178.
- 16 S. Pittalis, C. R. Proetto, A. Floris, A. Sanna, C. Bersier, K. Burke and E. K. U. Gross, *Physical Review Letters*, 2011, 107, 163001.
- 17 J. C. Smith, A. Pribram-Jones and K. Burke, *Phys. Rev. B*, 2016, 93, 245131.
- 18 T. Gould, J. Phys. Chem. Lett., 2020, 11, 9907-9912.
- 19 T. Gould, G. Stefanucci and S. Pittalis, *Physical Review Letters*, 2020, **125**, 233001.
- 20 B. Senjean and E. Fromager, *International Journal of Quantum Chemistry*, 2020, **120**, e26190.
- 21 N. Marzari, D. Vanderbilt and M. C. Payne, *Phys. Rev. Lett.*, 1997, **79**, 1337.
- 22 A. Ruiz-Serrano and C.-K. Skylaris, J. Chem. Phys., 2013, 139, 054107–1–054107–8.
- 23 C.-K. Skylaris, P. Haynes, A. Mostofi and M. Payne, *Journal of Chemical Physics*, 2005, **122**, 084119–1–084119–10.
- 24 J. Prentice et al., The Journal of Chemical Physics, 2020, 152, 174111–1–174111–36.
- 25 A. West, Computational and Theoretical Chemistry, 2014, 1045, 73–77.
- 26 M. J. S. Phipps, T. Fox, C. S. Tautermann and C.-K. Skylaris, Journal of Chemical Theory and Computation, 2016, 12, 3135– 3148.
- 27 H. Chen and C.-K. Skylaris, *Physical Chemistry Chemical Physics*, 2021, **23**, 8891.
- 28 C.-K. Skylaris, A. Mostofi, P. Haynes, O. Diéguez and M. Payne, *Physical Review*, 2002, 66, 035119–1–035119–12.
- 29 C. Freysoldt, S. Boeck and J. Neugebauer, *Phys. Rev. B*, 2009, 79, 241103.
- 30 F. Jensen, J. Chem. Phys., 2017, 146, 184109-1-184109-7.
- 31 P. Politzer and H. Weinstein, J. Chem. Phys., 1979, 71, 4218– 4220.
- 32 G. Del Re, P. Otto and J. Ladik, *Israel Journal of Chemistry*, 1980, **19**, 265–271.
- 33 Z. Szekeres and P. Surján, *Chemical Physics Letters*, 2003, 369, 125–130.

- 34 P. Haynes, C.-K. Skylaris, A. Mostofi and M. Payne, *Chemical Physics Letters*, 2006, **422**, 345–349.
- 35 A. Mostofi, P. Haynes, C.-K. Skylaris and M. Payne, *Journal of Chemical Physics*, 2003, **119**, 8842–8848.
- 36 R. Khaliullin, M. Head-Gordon and A. Bell, *The Journal of Chemical Physics*, 2006, **124**, 204105–1–204105–11.
- 37 C. Sanderson and R. Curtin, *Journal of Open Source Software*, 2016, 1, 26.
- 38 Q. Ge, Y. Mao and M. Head-Gordon, J. Chem. Phys., 2018, 148, 064105–1–064105–13.
- 39 J. F. Janak, The American Physical Society, 1978, 18, 7165– 7168.
- 40 R. Parr and W. Yang, *Density-Functional Theory of Atoms and Molecules*, Oxford University Press, 1989.
- 41 T. Ellaby, L. Briquet, M. Sarwar, D. Thompsett and C.-K. Skylaris, *The Journal of Chemical Physics*, 2019, **151**, 114702.
- 42 M. J. S. Phipps, T. Fox, C. S. Tautermann and C.-K. Skylaris, Journal of Chemical Theory and Computation, 2017, 13, 1837– 1850.
- 43 C. Peng, Journal of Materials Chemistry A, 2021, 9, 16798– 16804.