

OPTICAL AMPLIFIER TECHNOLOGIES IN NEW GENERATION OPTICAL SYSTEMS

David N Payne & R I Laming

**Optoelectronics Research Centre
The University
Southampton
SO9 5NH
Hampshire
United Kingdom**

Tel: (0703) 593583

Fax: (0703) 593142

The erbium-doped fibre amplifier (EDFA) has developed rapidly since its announcement in 1987. The EDFA is now established as a key component for future high-speed, silica-based optical fibre communication networks operating at a wavelength of $1.55\mu\text{m}$. Its major attributes are high gain, high efficiency, low noise and potential multichannel operation with low interchannel crosstalk. Expected applications are as fibre power-amplifiers in transmission systems and distribution networks, as signal repeaters in point-to-point optical links, as fibre pre-amplifiers in amplifier/receiver combinations and as distributed fibre amplifiers for soliton propagation.

As a result of its almost ideal amplifier performance and its wide applicability in telecommunications systems, the development of the amplifier as a component has already reached the point where today the EDFA can be considered as almost mature. Inevitably, therefore, further scope for major improvements is limited. However, there are a number of areas where enhanced performance may be expected in the future and which remain the subject of intensive worldwide investigation.

Pump Efficiency and Noise

Factors which have emerged as important in achieving maximum gain for minimum pump power (max. dB/mW) are fibre numerical aperture, erbium concentration and confinement, and background loss. Unfortunately, these factors are interrelated; it is found that increasing the numerical aperture increases the fibre background loss, especially for high erbium concentrations. The best reported result of 11dB/mW [1] was for a fibre made by the VAD process. Results which exceed this value have yet to be reported, although fibres made in our laboratory using the MCVD fabrication process have achieved 8.9dB/mW. However, it should be recognised that a trade-off exists between gain efficiency and noise figure [2] owing to backward-travelling ASE which saturates the input to the amplifier. Thus with the conventional (co-directionally pumped) configuration it is virtually impossible to obtain a combination of high gain ($> 30\text{dB}$) and quantum-limited NF. Incorporating an isolator in the middle of the EDFA overcomes these problems and we have demonstrated an amplifier with 54dB gain and 3.1dB NF for only 45mW of pump power.

High Output Power

The search for EDFA's with output power in excess of +20dBm depends largely upon the availability of a sufficiently-powerful and practical pump source. Approaches vary from the use of multiple-diode lasers [3], to the adoption of Nd:YAG mini-lasers [4] and Nd³⁺-doped fibre lasers [5]. The latter two emit at a wavelength around 1.06 μ m and can give output powers in excess of 1 Watt, thus showing considerable potential as pumps for EDFA's with output power approaching +30dBm. To exploit this pump wavelength requires an erbium/ytterbium co-doped fibre [6]. Recently, we have shown that it is also possible to directly pump an Er³⁺/Yb³⁺ amplifier or laser using a 1W 962nm multi-stripe diode using a cladding-pump configuration [7]. This is an extremely attractive route to high power operation of these devices and should be scalable to diode-pumped amplifiers giving in excess of 1W output.

Planar EDFA's

Although the planar waveguide approach to erbium-doped amplifiers is attractive particularly for lossless splitting of a signal into a large number of output ports, the search for a planar amplifier is plagued by erbium concentration effects which result in a large loss of radiative quantum efficiency once the erbium concentration exceeds a few hundred ppm. This effect limits the length of the amplifier to around a metre. The search continues to find a glass host which is able to accept a high level of erbium doping from which amplifiers of a few mm in length can be fabricated.

Soliton Generation

Several fibre laser soliton laser configurations have been reported, although most suffer from low repetition rates or pulse position uncertainty. Recently, a means whereby high-purity 70 Gbit/s cw soliton trains can be generated has been reported [8], using only two DFB laser diodes and an EDFA. The technique is based on the non-linear propagation and compression of a dual-frequency beat signal, amplified by an EDFA and propagated through a length of fibre having a dispersion-decreasing characteristic. The method is applicable to soliton train generation in the range 30-200 Gbit/s and yields mark space ratios from 1:5 to 1:11.

In conclusion, some areas remain for improvement before the ultimate EDFA is achieved. As the EDFA matures, attention is now switching to areas where obvious gains can be made, for example low-loss components (isolators, WDM couplers), system control and engineering issues.

References

1. M. Shimizu, M. Yamada, M. Horiguchi, T. Takeshita & M. Okayasu:
"Erbium-doped fibre amplifiers with an extremely-high gain efficient of 11.0dB/mW",
Electronics Letters, Vol. 26, pp. 1641-1642, 1990.
2. M.N. Zervas, R.I. Laming & D.N. Payne:
"Trade-off between gain efficiency and noise figure in an optimised fibre amplifier",
Proc. OFC'92, San Jose, February 1992.

3. H. Takenaka, H. Okuno, M. Fujita, Y. Odagiri, Y. Sunohara & I. Mito:
"Compact size and high output power Er-doped fibre amplifier modules pumped with 1.48 μ m MQW LDs",
Proc. Second Topical Meeting on Optical Amplifiers and Their Applications, pp. 254-257, Snowmass, Colorado, June 1991.
4. S.G. Grubb, T.H. Windhorn, W.F. Humer, K.L. Sweeney, P.A. Ielabady, J.E. Townsend, K.P. Jedrzejewski & W.L. Barnes:
"+20dBm erbium power amplifier pumped by a diode-pumped Nd:YAG laser",
Proc. Second Topical Meeting on Optical Amplifiers and Their Applications, Paper PDP 2-1, Snowmass, Colorado, June 1991.
5. J.D. Minelly, R.I. Laming, J.E. Townsend, W.L. Barnes E.R. Taylor, K.P. Jedrzejewski & D.N. Payne:
"High-gain fibre power amplifier tandem-pumped by a 3W multi-stripe diode",
Proc. OFC'92, San Jose, February 1992.
6. J.E. Townsend, W.L. Barnes, K.P. Jedrzejewski & S.G. Grubb:
"Yb³⁺-sensitised Er³⁺-doped optical fibre in silica host with very high transfer efficiency",
Electronics Letters, Vol. 27, pp. 1958-1959, 1991.
7. J.D. Minelly, W.L. Barnes, P.R. Morkel, J.E. Townsend, S.G. Grubb, D.N. Payne:
"High-power Er³⁺/Yb³⁺ fibre laser pumped by a 962nm diode-array",
Conference on Lasers and Electro-Optics (CLEO '92), No. PapPD, PDP, Anaheim, Ca., May 1992.
8. S.V. Chernikov, D.J. Richardson, R.I. Laming, E.M. Dianov, D.N. Payne:
"70Gbit/s fibre based source of fundamental solitons at 1500nm",
18th European Conference on Optical Communication, (ECOC'92), Berlin, 27 Sept-1 Oct 1992.